

INTERIOR ACOUSTIC SOLUTIONS

Acoustic & thermal insulation product selector for partitions and wall systems



Building acoustics are an important element in any design and consideration needs to be given to both sound absorption, the control of sound that is generated within a room, as well as sound transmission, sound that passes through a dividing wall or building element. Bradford Acoustigard products can assist in the control of acoustics, as well as delivering improvements in the thermal performance of the building structure.

THE BENEFITS OF ACOUSTIGARD™

There are various types of cladding and cavity in-fill systems that can assist in controlling noise in a building based upon their sound absorption and transmission properties. The Bradford Acoustigard range is suitable for use in a variety of these acoustic applications and as a thermally certified (according to AS/NZS4859:1) insulation material, it also contributes to the building's energy efficiency rating.

The Bradford Acoustigard product range has been designed to provide both a broad range of thicknesses to suit different cavity in-fill applications, as well as a substantial range of densities to meet acoustic and thermal specifications.

This ensures that the right combination of thickness, acoustic and/or thermal properties can be specified for most applications.

If you require assistance specifying Acoustigard, CSR Bradford's experienced technical team include on-staff engineering and architectural support to help you with specifying the right product, as well as access to CSR's Building Scientist. In selecting the most appropriate solution for your application, CSR Bradford always recommend that an acoustic engineer is consulted early in the project.

PARTITION WALLS SHAFT LINERS CEILING OVERLAYS

ACOUSTIGARD™ IS NON-COMBUSTIBLE*

A key requirement of the Building Code of Australia where fire performance is important is non-combustibility. This ensures that both installed, as well as unused bulk insulation stock stored on-site, is a minimal hazard to occupants and workers.

*Excludes 32 & 34Kg/m³ density products when tested in accordance with AS1530.1.

ACOUSTIGARD™ RESISTS SLUMPING IN THE CAVITY

The ability of insulation to resist slumping in the cavity is critical to ensure easy assembly and prevent un-insulated voids forming inside the wall cavity which can compromise acoustic and thermal performance.

ACOUSTIGARD™ COMPRESSION PACKS FOR EASY HANDLING ON SITE


Supplied to site in sealed compression packaging, Acoustigard products require minimal site storage space in comparison to polyester insulation products, thereby offering more material coverage for less material movement.

ACOUSTIGARD™ IS EASY TO WORK WITH

Acoustigard products are easy to cut around building services and won't bind or bunch if following trades drill into the wall cavity – this ensures that Acoustigard remains in position to provide optimum performance.



Polyester



Acoustigard

ACOUSTIC BAFFLES & CEILING OVERLAYS

The Acoustigard product range can be effectively used as an acoustic baffle above a partition wall or as ceiling overlay over ceiling tiles. Consideration should be given to the density of the product selected, colour of facing required to conceal the product and the weight capacity of the ceiling system prior to specification.

ZERO ODP

As referenced in the US EPA list of Ozone Depleting Substances (Class 1 and Class 2), no Ozone Depleting Substances are involved in either the manufacture or composition of Acoustigard products.

MADE IN AUSTRALIA FOR AUSTRALIAN CONDITIONS

Acoustigard™ products are developed and manufactured in Australia for Australian conditions, ensuring that they have been tested to withstand the broad climatic conditions.

SAFE TO HANDLE FBS-1 BIO-SOLUBLE INSULATION

Acoustigard™ products are manufactured from FBS-1 Glasswool Bio-Soluble Insulation, which is classified as non-hazardous according to the criteria of the Australian Safety and Compensation Council ASCC (formerly NOHSC). Further information can be found on the MSDS on the CSR Bradford website.

PRODUCT RANGE SELECTOR

ACOUSTIGARD 11 – Partition Roll 11kg/m³

GREEN TAG CERTIFIED

| Thickness (mm) | Density (kg/m ³) | Material R-Value (R _M) | Width (mm) | Roll length (m) | Rolls per pack | Area per pack (m ²) | Product Code |
|----------------|------------------------------|------------------------------------|------------|-----------------|----------------|---------------------------------|--------------|
| 50 | 11 | R1.2 | 450 | 16.2 | 3 | 21.9 | 119466 |
| 50 | 11 | R1.2 | 600 | 16.2 | 2 | 19.4 | 119467 |
| 75 | 11 | R1.7 | 450 | 13.5 | 3 | 18.2 | 119468 |
| 75 | 11 | R1.7 | 600 | 13.5 | 2 | 16.2 | 119469 |
| 110 | 11 | R2.5 | 600 | 8.1 | 2 | 9.7 | 119511 |
| 165 | 11 | R3.5 | 600 | 5.4 | 2 | 6.5 | 119470 |

ACOUSTIGARD 14 – Partition Roll 14kg/m³

GREEN TAG CERTIFIED

| Thickness (mm) | Density (kg/m ³) | Material R-Value (R _M) | Width (mm) | Roll length (m) | Rolls per pack | Area per pack (m ²) | Product Code |
|----------------|------------------------------|------------------------------------|------------|-----------------|----------------|---------------------------------|--------------|
| 50 | 14 | R1.3 | 450 | 16.2 | 3 | 21.9 | 119521 |
| 50 | 14 | R1.3 | 600 | 16.2 | 2 | 19.4 | 119522 |
| 75 | 14 | R1.8 | 450 | 13.5 | 3 | 18.2 | 119523 |
| 75 | 14 | R1.8 | 600 | 13.5 | 2 | 16.2 | 119524 |
| 90 | 14 | R2.2 | 450 | 10.8 | 3 | 14.6 | 73776 |
| 90 | 14 | R2.2 | 600 | 10.8 | 2 | 13.0 | 87731 |
| 100 | 14.5 | R2.5 | 450 | 10.8 | 3 | 14.6 | 119527 |
| 100 | 14.5 | R2.5 | 600 | 10.8 | 2 | 13.0 | 119526 |

ACOUSTIGARD 18 – Partition Roll 18kg/m³

Please note, minimum order quantities may apply

| Thickness (mm) | Density (kg/m ³) | Material R-Value (R _M) | Width (mm) | Roll length (m) | Rolls per pack | Area per pack (m ²) | Product Code |
|----------------|------------------------------|------------------------------------|------------|-----------------|----------------|---------------------------------|--------------|
| 25 | 18 | R0.7 | 600 | 21.6 | 2 | 25.9 | 119373 |
| 50 | 18 | R1.3 | 450 | 10.8 | 3 | 14.6 | 119375 |
| 50 | 18 | R1.3 | 600 | 10.8 | 2 | 13.0 | 119376 |
| 75 | 18 | R2.0 | 450 | 8.1 | 3 | 10.9 | 119377 |
| 75 | 18 | R2.0 | 600 | 8.1 | 2 | 9.7 | 119379 |

ACOUSTIGARD 20 – Partition Roll 20kg/m³

Please note, minimum order quantities may apply

| Thickness (mm) | Density (kg/m ³) | Material R-Value (R _M) | Width (mm) | Roll length (m) | Rolls per pack | Area per pack (m ²) | Product Code |
|----------------|------------------------------|------------------------------------|------------|-----------------|----------------|---------------------------------|--------------|
| 50 | 20 | R1.4 | 450 | 10.8 | 3 | 14.6 | 119413 |
| 50 | 20 | R1.4 | 600 | 10.8 | 2 | 13.0 | 119414 |
| 75 | 20 | R2.0 | 450 | 8.1 | 3 | 10.9 | 119444 |
| 75 | 20 | R2.0 | 600 | 8.1 | 2 | 9.7 | 119446 |
| 90 | 20 | R2.5 | 450 | 5.4 | 3 | 7.3 | 119462 |
| 90 | 20 | R2.5 | 600 | 5.4 | 2 | 6.5 | 119463 |

ACOUSTIGARD 24 – Partition Roll 24kg/m³

Please note, minimum order quantities may apply

| Thickness (mm) | Density (kg/m ³) | Material R-Value (R _M) | Width (mm) | Roll length (m) | Rolls per pack | Area per pack (m ²) | Product Code |
|----------------|------------------------------|------------------------------------|------------|-----------------|----------------|---------------------------------|--------------|
| 50 | 24 | R1.4 | 450 | 10.8 | 3 | 14.6 | 119529 |
| 50 | 24 | R1.4 | 600 | 10.8 | 2 | 13.0 | 119528 |
| 75 | 24 | R2.1 | 450 | 8.1 | 3 | 10.9 | 119530 |
| 75 | 24 | R2.1 | 600 | 8.1 | 2 | 9.7 | 119551 |

ACOUSTIGARD 32 – Partition Roll 32kg/m³

Please note, minimum order quantities may apply

| Thickness (mm) | Density (kg/m ³) | Material R-Value (R _M) | Width (mm) | Roll length (m) | Rolls per pack | Area per pack (m ²) | Product Code |
|----------------|------------------------------|------------------------------------|------------|-----------------|----------------|---------------------------------|--------------|
| 50 | 32 | R1.5 | 450 | 8.1 | 3 | 10.9 | 119587 |
| 50 | 32 | R1.5 | 600 | 8.1 | 2 | 9.7 | 119588 |
| 75 | 32 | R2.2 | 450 | 5.4 | 3 | 7.3 | 119589 |
| 75 | 32 | R2.2 | 600 | 5.4 | 2 | 6.5 | 119631 |

ACOUSTIGARD – Partition Batts

Please note, minimum order quantities may apply

| Thickness (mm) | Density (kg/m ³) | Material R-Value (R _M) | Width (mm) | Batt length (mm) | Batts per pack | Area per pack (m ²) | Product Code |
|----------------|------------------------------|------------------------------------|------------|------------------|----------------|---------------------------------|--------------|
| 90 | 34 | R2.7 | 450 | 1160 | 5 | 2.6 | 118843 |
| 110 | 11 | R2.5 | 580 | 1160 | 12 | 8.1 | 120054 |

ACOUSTIC PERFORMANCE

Specific wall system acoustic performance information is available by contacting CSR Bradford.

| Thickness (mm) | Density (kg/m ³) | Frequency (Hz) | | | | | | | | |
|-------------------|---------------------------------|----------------|------|------|------|------|------|------|------|------------|
| | | 125 | 250 | 500 | 1000 | 2000 | 4000 | 5000 | NRC | α_w |
| 75 | 11 | 0.26 | 0.63 | 0.97 | 0.87 | 0.92 | 0.97 | 0.95 | 0.85 | 0.90 |
| 75 | 14 | 0.26 | 0.71 | 1.03 | 1.00 | 0.95 | 0.99 | 0.97 | 0.90 | 0.95 |

Sound absorption results tested in accordance with AS1045:1998 and NRC results tested in accordance with ASTM C423-90A.

FIRE RESISTANCE

When tested in accordance with AS1530 Part 1:1994, Acoustigard products up to a density of 24kg/m³ are non-combustible.

FIRE HAZARD PROPERTIES

When tested in accordance with AS1530.3:1999

| Product | Ignitability | Spread of Flame | Heat Evolved | Smoke Developed |
|-------------------|--------------|-----------------|--------------|-----------------|
| Acoustigard Range | 0 | 0 | 0 | 1 |

SPECIFYING ACOUSTIGARD™

To ensure that Bradford Acoustigard is specified correctly, please include the following details on all drawings and specification information:

The insulation material shall be Bradford Acoustigard FBS-1 Glasswool insulation, having a material R-Value of **R_m**_____ (specify R-Value) @ _____mm (specify thickness) with a nominal density of _____**kg/m³** (specify density).

DO YOU NEED TECHNICAL ASSISTANCE?

For more information call **1300 887 160** or visit **www.bradfordinsulation.com.au**

Bradford™
for smarter environments

CSR Bradford

55 Stennett Rd, Ingleburn NSW 2565 Australia
Telephone 1300 887 160 Facsimile (02) 9765 7002
www.bradfordinsulation.com.au

CSR Bradford is a business division of CSR Building Products Limited ABN 55 008 631 356

The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Bradford. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the CSR Bradford website for the latest revision of this document. The purchaser should independently determine the suitability of the product for the intended use and application.